APPLICATIONS



DECKS IN SHIPS



INDUSTRIAL FLOORING



PEDESTRIAN BRIDGES



FLOORING IN SEMI-TRAILERS



LOAD-BEARING PLATFORMS



FLOORING IN COMMERCIAL VEHICLES

TECHNICAL SPECIFICATIONS

Panel sizes, L×W, mm (ft)	2440×1220×2440/2500×1250×2500 (8×4×8) 1500×3000/1525×3050 (5×10)	
Thickness, mm	6-30 (thicknesses up to 40 mm on request)	
Surface	W/F (mesh/smooth)	
Wear resistance, Taber value (EN 438-2:2016)	at least 2,600R	
Wheel test value (SFS 3939)	at least 10,000 movements	
Slip resistance rating (DIN 51130)	R13	
Coating color	Black (W)/Black, Dark Brown (F)	
Coating density	Black (125 g/m²)/Dark Brown (120 g/m²)	
Edge treatment	painting on request	
Formaldehyde emission class	E1	
Water resistance	high	
Density, kg/m³	640-700	
Moisture, %	≤14	

Cutting to size and CNC-machining of edges and surfaces available on request. Manufactured to STO Film-Faced Birch Plywood. The STO document is available in the Documents section at www.sveza.com.


STRENGTH VALUES

Parameter	Thickness, mm	Value
Static bending strength, min MPa	l l	
- along the grain of the face veneers	0.70	60
- across the grain of the face veneers	9 - 30	30
Tensile strength along the grain, min MPa	6-8	30
Modulus of elasticity in static bending, min MPa		
- along the grain	0.70	6,000
- across the grain	9 - 30	3,000





SVEZA TITAN



BIRCH PLYWOOD WITH ABRASIVE SURFACE





RELIABLE FLOORING FOR RELIABLE TRANSPORTATION

Corundum particles









Wheel test value

> 10,000

э.





BIRCH PLYWOOD COVERED WITH SPECIAL ABRASIVE MATERIAL

Superior wear and slip resistance for commercial flooring applications to protect people from falling and cargo from shifting in transit

KEY BENEFITS



100% birch plywood



R13

SVEZA Titan's coating has corundum particles for superior wear and slip resistance

Highest anti-slip rating R13 (DIN 51130)

Compliance with the European load security requirements (EN 12195-1)







TESTED AND CERTIFIED

IWT BREMEN, GERMANY



Superior resistance to heavy rolling load (wheel test value: over 10,000 movements, SFS 3939)

Excellent wear resistance (Taber value: at least 2,600R, EN 438-2:2016]*

*Taber value 5 times higher than that of SVEZA's W/F regular film-faced plywood.

Moisture-resistant adhesive

